

BUPLen® 6131

Polypropylene Homopolymer

LUKOIL Bulgaria Ltd.

Message:

The polypropylene is granulated, stabilized normally and in natural colour.

It is used for textile and paper impregnation and production of monofilaments at high processing speed.

General Information			
Additive	Unspecified Stabilizer		
Features	Fast Molding Cycle		
	Good Stability		
	Homopolymer		
Uses	Monofilaments		
Appearance	Natural Color		
Forms	Granules		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.899 to 0.906	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) ¹ (230°C/2.16 kg)	25	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ²	> 29.0	MPa	ASTM D638
Flexural Modulus - 1% Secant	> 1100	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	> 50.0	°C	ASTM D648
NOTE			
1.	Procedure A		
2.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT