

Radilon® AL 200 Natural

Polyamide 66

Radici Plastics

Message:

Radilon® AL 200 Natural is a Polyamide 66 (Nylon 66) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Important attributes of Radilon® AL 200 Natural are:

Flame Rated

Heat Resistant

General Information				
Features	Good Heat Aging Resistance			
Appearance	Natural Color			
Resin ID (ISO 1043)	PA6.6-I			
Physical	Dry	Conditioned	Unit	Test Method
Density	1.12	--	g/cm ³	ISO 1183
Water Absorption ¹ (Equilibrium, 23°C, 1.00 mm, 50% RH)	2.4 to 2.8	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	2700	1200	MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	65.0	45.0	MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	6.0	15	%	ISO 527-2/1A/50
Flexural Modulus ²	2400	950	MPa	ISO 178
Flexural Stress ³	90.0	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	12	--	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break	No Break		ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	200	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	65.0	--	°C	ISO 75-2/A
Melting Temperature ⁴	260	--	°C	ISO 3146
Flammability	Dry	Conditioned		Test Method
Flame Rating	HB	--		UL 94
NOTE				
1.	Saturation			
2.	2.0 mm/min			
3.	2.0 mm/min			
4.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

