

Leona™ 54G33

Polyamide 66

Asahi Kasei Chemicals Corporation

Message:

Leona™ 54G33 is a Polyamide 66 (Nylon 66) product filled with 33% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, or North America. Applications of Leona™ 54G33 include automotive, engineering/industrial parts, fabrics/fibers and industrial applications.

Characteristics include:

Flame Rated

Good Aesthetics

High Stiffness

High Strength

General Information	
UL YellowCard	E48285-240898
Filler / Reinforcement	Glass Fiber,33% Filler by Weight
Features	High Stiffness
	High Strength
	Pleasing Surface Appearance
Uses	Automotive Applications
	Fabrics
	Industrial Applications
	Structural Parts

Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.39	--	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage				Internal Method
Across Flow	0.90	--	%	
Flow	0.40	--	%	
Water Absorption				
Saturation, 23°C	--	1.9	%	
Equilibrium, 23°C, 50% RH	--	1.9	%	ISO 62
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness				ASTM D785, ISO 2039-2
M-Scale	93	68		
R-Scale	120	110		
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	9700	6100	MPa	ISO 527-2
Tensile Stress				
Break, 23°C	183	113	MPa	ISO 527-2
--	181	118	MPa	ASTM D638

Tensile Elongation				
Break	3.0	7.0	%	ASTM D638
Break, 23°C	4.0	9.0	%	ISO 527-2
Flexural Modulus				
--	9100	5000	MPa	ASTM D790
23°C	9000	5300	MPa	ISO 178
Flexural Strength				
--	289	167	MPa	ASTM D790
23°C	270	165	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	12	19	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	98	98	kJ/m ²	ISO 179
Notched Izod Impact	140	200	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, Unannealed	250	--	°C	ASTM D648, ISO 75-2/B
1.8 MPa, Unannealed	240	--	°C	ASTM D648
1.8 MPa, Unannealed	230	--	°C	ISO 75-2/A
CLTE - Flow	3.0E-5	--	cm/cm/°C	ASTM D696
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+15	--	ohms	ASTM D257, IEC 60093
Volume Resistivity				
--	1.0E+15	--	ohms·cm	ASTM D257
23°C	1.0E+15	--	ohms·cm	IEC 60093
Dielectric Strength	31	--	kV/mm	ASTM D149, IEC 60243-1
Comparative Tracking Index (3.00 mm)	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.750 mm)	HB	--		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT