

LG ASA LI923

Acrylonitrile Styrene Acrylate

LG Chem Ltd.

Message:

Description:
Good Weatherability, High Rigidity
Application:
Communication Instrument Cover, Cable Connecting Cover, Door Panel

General Information			
UL YellowCard	E67171-248323		
Features	Rigidity, high		
	Good weather resistance		
Uses	Communication Equipment		
Forms	Particle		
Processing Method	Extrusion		
Multi-Point Data	Specific Heat vs. Temperature (ISO 11403-2)		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.06	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	5.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.40 - 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	103		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹ (3.20 mm)	2150	MPa	ASTM D638
Tensile Strength ² (Yield, 3.20 mm)	47.1	MPa	ASTM D638
Tensile Elongation ³			ASTM D638
Yield, 3.20mm	> 6.0	%	ASTM D638
Fracture, 3.20mm	25	%	ASTM D638
Flexural Modulus ⁴ (3.20 mm)	2160	MPa	ASTM D790
Flexural Strength ⁵ (3.20 mm)	77.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.20 mm	39	J/m	ASTM D256
-30°C, 6.40 mm	39	J/m	ASTM D256
23°C, 3.20 mm	250	J/m	ASTM D256
23°C, 6.40 mm	180	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648

0.45 MPa, unannealed, 6.40mm	97.0	°C	ASTM D648
1.8 MPa, unannealed, 6.40mm	89.0	°C	ASTM D648
Vicat Softening Temperature	96.0	°C	ASTM D1525 ⁶
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.60 mm	HB		UL 94
3.20 mm	HB		UL 94
Extrusion	Nominal Value	Unit	
Drying Temperature	80.0 - 90.0	°C	
Drying Time	2.0 - 3.0	hr	
Cylinder Zone 1 Temp.	190 - 200	°C	
Cylinder Zone 2 Temp.	200 - 220	°C	
Cylinder Zone 3 Temp.	210 - 230	°C	
Cylinder Zone 4 Temp.	210 - 230	°C	
Adapter Temperature	210 - 230	°C	
Melt Temperature	200 - 230	°C	
Die Temperature	210 - 250	°C	
Extrusion instructions			
Minimum Moisture Content: 0.01%Roll Stack Temperature: Top: 70 to 90 °C Middle: 70 to 90 °C Bottom: 70 to 100 °C			
NOTE			
1.	1.0 mm/min		
2.	50 mm/min		
3.	50 mm/min		
4.	15 mm/min		
5.	15 mm/min		
6.	速率 A (50°C/h), 载荷2 (50N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT