

VENYL UG207 - 8071

Polyamide 66

AD majoris

Message:

VENYL UG207 - 8071 is a 20% glass fibre reinforced polyamide 66 intended for Injection moulding.

APPLICATIONS

VENYL UG207 - 8071 has been developed especially for very demanding applications in automotive industry and electrical parts.

Products requiring excellent combination between thermal and mechanical properties.

VENYL UG207 - 8071 is available in both black standard (VENYL UG207 - 8229) and natural (VENYL UG207) but other colours can be provided on request.

General Information				
Filler / Reinforcement		Glass Fiber,20% Filler by Weight		
Features		Recyclable Material		
Uses		Automotive Applications		
		Electrical Parts		
Appearance		Black		
		Colors Available		
		Natural Color		
Forms		Pellets		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.27	--	g/cm ³	ISO 1183
Molding Shrinkage	0.60 to 0.90	--	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	1.8	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (L-Scale)	108	102		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	7000	4750	MPa	ISO 527-2
Tensile Stress (Break)	125	80.0	MPa	ISO 527-2
Tensile Strain (Break)	3.0	3.0	%	ISO 527-2
Flexural Modulus	6000	3750	MPa	ISO 178
Flexural Stress	210	170	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	6.0	10	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	25	35	kJ/m ²	ISO 179
Notched Izod Impact	75	120	J/m	ISO 180
Thermal	Dry	Conditioned	Unit	Test Method

Heat Deflection Temperature				
0.45 MPa, Unannealed	252	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	241	--	°C	ISO 75-2/A
Melting Temperature (DSC)	256	--	°C	ISO 3146
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13	1.0E+11	ohms	DIN 53482
Volume Resistivity	1.0E+14	1.0E+12	ohms·cm	DIN 53482
Comparative Tracking Index (Solution A)	> 500	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.60 mm)	HB	--		UL 94
Glow Wire Flammability Index (2.00 mm)	750	--	°C	IEC 60695-2-12
Oxygen Index	25	--	%	ISO 4589-2
Injection	Dry	Unit		
Rear Temperature	285 to 300		°C	
Middle Temperature	280 to 295		°C	
Front Temperature	275 to 290		°C	
Nozzle Temperature	265 to 280		°C	
Mold Temperature	90.0 to 120		°C	
Injection Pressure	85.0 to 110		MPa	
Injection Rate	Fast			
Holding Pressure	50.0 to 70.0		MPa	
Screw L/D Ratio	15.0:1.0 to 20.0:1.0			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT