

Rotec® ABS 1002 FR V0/5

Acrylonitrile Butadiene Styrene

ROMIRA GmbH

Message:

Rotec® ABS 1002 FR V0/5 is an acrylonitrile butadiene styrene (ABS) material. This product is available in Europe, and the processing method is injection molding.

Rotec® The main features of ABS 1002 FR V0/5 are:

flame retardant/rated flame

Flame Retardant

General Information			
UL YellowCard	E148878-101031222		
Additive	Flame retardancy		
Features	Flame retardancy		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.18	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	37	g/10 min	ISO 1133
Molding Shrinkage (23°C)	0.40 - 0.70	%	ISO 294-4
Water Absorption (23°C, 24 hr)	0.30	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2200	MPa	ISO 527-2/1
Tensile Stress (23°C)	38.0	MPa	ISO 527-2/50
Tensile Strain (Break, 23°C)	35	%	ISO 527-2/50
Flexural Modulus ¹ (23°C)	2100	MPa	ISO 178
Flexural Stress ² (23°C)	61.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	14	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	85	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	81.0	°C	ISO 75-2/A
Vicat Softening Temperature	88.0	°C	ISO 306/B50
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.5 mm	V-0		UL 94
	V-0		
3.0 mm	5VA		UL 94
NOTE			

1.	2.0 mm/min
2.	2.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

