

TOTAL Polyethylene HDPE 2287

High Density (HMW) Polyethylene

TOTAL Refining & Chemicals

Message:

TOTAL Polyethylene 2287 is a High Density Polyethylene material. It is available in North America.

Important attributes of TOTAL Polyethylene 2287 are:

REACH Compliant

Good Processability

Good Tear Strength

High Molecular Weight

Impact Resistant

Typical applications include:

Bags/Liners

Film

Food Contact Applications

General Information			
Features	Good Processability		
	Good Tear Strength		
	High Density		
	High Impact Resistance		
	High Molecular Weight		
	Med.-Wide Molecular Weight Distrib.		
Uses	Bags		
	Film		
	Food Wrap		
	Liners		
Agency Ratings	EC 1907/2006 (REACH)		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.951	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR)			ASTM D1238
190°C/2.16 kg	0.080	g/10 min	
190°C/21.6 kg	10	g/10 min	
190°C/5.0 kg	0.32	g/10 min	
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	20	µm	
Secant Modulus ¹			ASTM D882A
2% Secant, MD : 20 µm, Blown Film	841	MPa	
2% Secant, TD : 20 µm, Blown Film	910	MPa	
Tensile Strength ²			ASTM D882A

MD : Yield,20 μm, Blown Film	36.5	MPa	
TD : Yield,20 μm, Blown Film	34.5	MPa	
MD : Break, 20 μm,Blown Film	63.4	MPa	
TD : Break, 20 μm,Blown Film	67.6	MPa	
Tensile Elongation ³			ASTM D882A
MD : Break, 20 μm,Blown Film	300 to 500	%	
TD : Break, 20 μm,Blown Film	300 to 500	%	
Dart Drop Impact (20 μm, Blown Film)	350	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 20 μm, Blown Film	24	g	
TD : 20 μm, Blown Film	120	g	
Water Vapor Transmission Rate (38°C, 20 μm, Blown Film)	12	g/m ² /24 hr	ASTM F1249
Thermal	Nominal Value	Unit	Test Method
Peak Melting Temperature	132	°C	ASTM D3418
NOTE			
1.	510 mm/min		
2.	510 mm/min		
3.	510 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

