

GLS ABS SG59

Acrylonitrile Butadiene Styrene

GLS Polymers Pvt. Ltd.

Message:

ABS 25 GF Precolor

General Information			
Filler / Reinforcement	Glass Fiber,25% Filler by Weight		
Appearance	Colors Available		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22 to 1.23	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	> 8.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.10 to 0.20	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	> 6500	MPa	ASTM D638
Tensile Strength ¹ (Yield)	> 80.0	MPa	ASTM D638
Flexural Modulus	> 5200	MPa	ASTM D790
Flexural Strength	> 90.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	> 50	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	> 105	°C	
1.8 MPa, Unannealed	> 102	°C	
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	205 to 235	°C	
Mold Temperature	60.0 to 85.0	°C	
Injection Pressure	69.0 to 102	MPa	
NOTE			
1.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

