

Hyundai EP PA66 LD460Z

Polyamide 66
HYUNDAI EP Co., Ltd.

Message:

Hyundai EP PA66 LD460Z is a Polyamide 66 (Nylon 66) product. It is available in Asia Pacific. Applications of Hyundai EP PA66 LD460Z include electrical/electronic applications and wire & cable.

Characteristics include:

- Flame Rated
- Flame Retardant
- Fast Molding Cycle

General Information			
Additive	Flame Retardant		
Features	Fast Molding Cycle		
	Flame Retardant		
	Good Electrical Properties		
Uses	Electrical/Electronic Applications		
	Insulation		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.40	g/cm ³	ASTM D1505
Ash Content	30	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	121		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	93.2	MPa	ASTM D638
Flexural Modulus	5300	MPa	ASTM D790
Flexural Strength	157	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	74	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	245	°C	ASTM D648
Melting Temperature	265	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+13 to 1.0E+15	ohms · cm	ASTM D257
Dielectric Strength	4.0	kV/mm	ASTM D149
Comparative Tracking Index (CTI)	PLC 2		UL 746
High Amp Arc Ignition (HAI)	PLC 0		UL 746

High Voltage Arc Resistance to Ignition (HVAR)	PLC 6	UL 746	
High Voltage Arc Tracking Rate (HVTR)	PLC 1	UL 746	
Hot-wire Ignition (HWI)	PLC 4	UL 746	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.750 mm, All Colors)	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

