

DOMAMID® 66GM305H

Polyamide 66

DOMO Engineering Plastics SPA

Message:

Polyamide 66, 30% glass fibre and mineral filler, heat stabilized, for injection moulding.

General Information			
Filler / Reinforcement	Glass\Mineral,30% Filler by Weight		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6500	MPa	ISO 527-2/1
Tensile Stress (Break)	130	MPa	ISO 527-2/5
Tensile Strain (Break)	3.5	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	6.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	250	°C	ISO 306/B50
Melting Temperature	258 to 262	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Burning Rate	< 100	mm/min	FMVSS 302
Flame Rating (0.800 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	75.0 to 85.0	°C	
Drying Time	4.0 to 6.0	hr	
Processing (Melt) Temp	260 to 285	°C	
Mold Temperature	70.0 to 120	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

