

PRL PPX-G20-(color)N

Polyphenylene Ether + PS

Polymer Resources Ltd.

Message:

This product has been certified for potable water applications up to 82C. Available in Black or Grey.

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Hydrolytically Stable		
	Low to No Water Absorption		
	Medium Heat Resistance		
Agency Ratings	NSF 61		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/11.6 kg)	1.0 to 8.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.20 to 0.50	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (L-Scale)	106		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 3.18 mm	93.1	MPa	
Break, 3.18 mm	93.1	MPa	
Tensile Elongation (Break, 3.18 mm)	3.0	%	ASTM D638
Flexural Modulus (3.18 mm)	5170	MPa	ASTM D790
Flexural Strength (3.18 mm)	138	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.3	kJ/m ²	ISO 179/1
Notched Izod Impact			
-30°C, 3.18 mm	53	J/m	ASTM D256
23°C, 3.18 mm	80	J/m	ASTM D256
23°C	6.3	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	138	°C	
1.8 MPa, Unannealed, 3.18 mm	132	°C	

Vicat Softening Temperature	143	°C	ASTM D1525 ¹
RTI Elec			UL 746
1.59 mm	65.0	°C	
3.18 mm	65.0	°C	
RTI Imp			UL 746
1.59 mm	65.0	°C	
3.18 mm	65.0	°C	
RTI Str			UL 746
1.59 mm	65.0	°C	
3.18 mm	65.0	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.59 mm	HB		
3.18 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	104 to 110	°C	
Drying Time	3.0 to 4.0	hr	
Drying Time, Maximum	8.0	hr	
Rear Temperature	260 to 304	°C	
Middle Temperature	271 to 310	°C	
Front Temperature	282 to 316	°C	
Processing (Melt) Temp	288 to 316	°C	
Mold Temperature	71.1 to 104	°C	
NOTE			

1. Rate B (120°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

