KMI PP KM-0284ZW

Polypropylene Impact Copolymer

KMI Group, Inc.

Message:

KM-0284ZW is a nucleated impact copolymer polypropylene for injection molding. Applications:

Thin walled applications such as housewares, and compounding

General Information			
Additive	Nucleating agent		
Features	Nucleated		
	Impact copolymer		
Uses	Thin wall parts		
	Composite		
	Household goods		
Processing Method	Composite		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	35	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	27.6	MPa	ASTM D638
Tensile Elongation (Break)	6.0	%	ASTM D638
Flexural Modulus	1380	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	80	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45			
MPa, Unannealed)	100	°C	ASTM D648
Melting Temperature	160 - 165	°C	Internal method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

