

Starpylen MF003SU

Polypropylene
Eurostar Engineering Plastics

Message:

Starpylen MF003SU is 15% Glass Fiber Reinforced Polypropylene Injection Molding Resin (also known as Starpylen WX 15V S34/3/040)

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.00	g/cm ³	ASTM D792
Molding Shrinkage - Flow (4.00 mm)	0.10 to 0.30	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3800	MPa	ISO 527-2/1
Tensile Stress (Yield)	60.0	MPa	ISO 527-2/50
Tensile Strain (Yield)	3.5	%	ISO 527-2/50
Flexural Modulus ¹	2900	MPa	ISO 178
Flexural Stress	70.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ² (23°C)	5.3	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ³ (23°C)	30	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁴ (1.8 MPa, Unannealed, 64.0 mm Span)	102	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	70.0	°C	
Drying Time	3.0	hr	
Rear Temperature	195 to 205	°C	
Middle Temperature	215 to 225	°C	
Front Temperature	225 to 250	°C	
Processing (Melt) Temp	225 to 250	°C	
Mold Temperature	30.0 to 50.0	°C	
NOTE			
1.	2.0 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT