

LG ASA LI931

Acrylonitrile Styrene Acrylate

LG Chem Ltd.

Message:

Description
Low Gloss, Extrusion
Application
Industrial Materials (Window Profile, Tile Etc)

General Information			
Features	Gloss, low		
Uses	Industrial application		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.07	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	7.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.40 - 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	81		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	32.4	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	65	%	ASTM D638
Flexural Modulus ³ (6.40 mm)	1520	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 6.40 mm)	49.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.20 mm	49	J/m	ASTM D256
-30°C, 6.40 mm	39	J/m	ASTM D256
23°C, 3.20 mm	98	J/m	ASTM D256
23°C, 6.40 mm	9.0	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 6.40mm ⁵	85.0	°C	ASTM D648
0.45 MPa, unannealed, 6.40mm ⁶	79.0	°C	ASTM D648
Vicat Softening Temperature	86.0	°C	ASTM D1525 ⁷
Optical	Nominal Value		Test Method
Gloss (45°)	30		ASTM D2457
Extrusion	Nominal Value	Unit	
Drying Temperature	70.0 - 80.0	°C	
Drying Time	3.0 - 4.0	hr	

Suggested Max Moisture	< 0.010	%
Cylinder Zone 1 Temp.	180 - 210	°C
Cylinder Zone 2 Temp.	190 - 230	°C
Cylinder Zone 3 Temp.	200 - 250	°C
Cylinder Zone 4 Temp.	200 - 250	°C
Adapter Temperature	200 - 250	°C
Melt Temperature	200 - 250	°C
Die Temperature	200 - 250	°C

Extrusion instructions

Top RollStack Temperature: 70 to 100°C Middle RollStack Temperature: 70 to 90°C Bottom RollStack Temperature: 60 to 90°C

NOTE

- | | |
|----|--------------------------|
| 1. | 50 mm/min |
| 2. | 50 mm/min |
| 3. | 15 mm/min |
| 4. | 15 mm/min |
| 5. | 4.6kg |
| 6. | 18.6kg |
| 7. | 速率 A (50°C/h), 载荷2 (50N) |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

