

PEXLOY™ PXP-315UV-BK10

Polycarbonate + Polyester

Pier One Polymers, Inc.

Message:

PEXLOY™ PXP 315UV is available in natural and custom colors, internal and external lubricants. Further information and details are available upon request.

General Information			
Additive	UV Stabilizer		
Features	Good UV Resistance		
	High Impact Resistance		
	Low Temperature Impact Resistance		
Appearance	Black		
	Colors Available		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.17	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	3.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	49.7	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	100	%	ASTM D638
Flexural Modulus (23°C)	2140	MPa	ASTM D790
Flexural Strength (23°C)	79.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-40°C	510	J/m	
23°C	800	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	96.0	°C	ASTM D648
Injection	Nominal Value	Unit	
Suggested Max Moisture	< 0.020	%	
Processing (Melt) Temp	243 to 279	°C	
Mold Temperature	65.0 to 82.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT