ISOTHANE® 1085A-E

Thermoplastic Polyurethane Elastomer (Polyester)

Great Eastern Resins Industrial Co Ltd (GRECO)

Message:

ISOTHANE 1085A-E product is polyester poly(adipate)ester based thermoplastic polyurethanes. It exhibits excellent transparency, toughness, abrasive resistance, and solvent resistance. The product can be blow molded.

General Information			
Features	Good Abrasion Resistance		
	Good Toughness		
	Solvent Resistant		
Appearance	Clear/Transparent		
Processing Method	Blow Molding		
	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	84		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Taber Abrasion Resistance (H-22 Wheel)	45.0	mg	ASTM D1044
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (300% Strain)	9.00	MPa	ASTM D412
Tensile Strength (Yield)	40.0	MPa	ASTM D412
Tensile Elongation (Break)	670	%	ASTM D412
Tear Strength ¹	103	kN/m	ASTM D624
Compression Set			ASTM D395B
23°C, 22 hr	30	%	
70°C, 22 hr	75	%	
NOTE			
1.	Die C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

