

CALIBRE™ 301 HMR FC030003

Polycarbonate Resin

Trinseo

Message:

CALIBRE™ 301 HMR FC030003 Polycarbonate resin offers exceptional impact resistance, heat distortion resistance, and optical clarity. CALIBRE 301 HMR also has a mold release package designed to improve processing larger more complex injection molded parts.

Applications:

Small & large appliances

General Information			
Additive	Mold Release		
Features	High Clarity		
	High Impact Resistance		
Uses	Appliances		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183/B
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	19	g/10 min	ISO 1133
Molding Shrinkage - Flow	0.50 to 0.70	%	ISO 294-4
Water Absorption			ISO 62
23°C, 24 hr	0.15	%	
Equilibrium, 23°C, 50% RH	0.32	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ISO 2039-2
M-Scale	73		
R-Scale	118		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ISO 527-2/50
Tensile Stress			ISO 527-2/50
Yield	60.0	MPa	
Break	71.0	MPa	
Tensile Strain			ISO 527-2/50
Yield	6.0	%	
Break	150	%	
Flexural Modulus ¹	2400	MPa	ISO 178
Flexural Stress ²	97.0	MPa	ISO 178
Taber Abrasion Resistance	45	%	ISO 9352
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA

-30°C	12	kJ/m ²	
23°C	25	kJ/m ²	
Notched Izod Impact Strength (23°C)	83	kJ/m ²	ISO 180/A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Annealed	143	°C	ISO 75-2/B
1.8 MPa, Unannealed	124	°C	ISO 75-2/A
1.8 MPa, Annealed	140	°C	ISO 75-2/A
Vicat Softening Temperature	148	°C	ISO 306/B50
Ball Indentation Temperature	> 125	°C	IEC 60335-1
CLTE - Flow	7.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Electric Strength	17	kV/mm	IEC 60243-1
Dielectric Constant			
60 Hz	3.00		IEC 60250
1 MHz	3.00		IEC 60250
100 Hz	3.00		IEC 60250
Dissipation Factor			IEC 60250
50 Hz	1.0E-3		
1 MHz	2.0E-3		
Comparative Tracking Index (2.00 mm, Solution A)	250	V	IEC 60112
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.586		ISO 489
Transmittance	89.0	%	ASTM D1003
Haze	1.0	%	ASTM D1003
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT