

OTECH PVC OW838 - Cable Jacket

Polyvinyl Chloride
OTECH Corporation

Message:
TRAY CABLE JACKET COMPOUNDS
Applications
STANDARD TRAY CABLE JACKET

General Information		
Uses	Jacketing	
	Wire & Cable Applications	
Physical	Nominal Value	Unit
Specific Gravity	1.38	g/cm ³
Hardness	Nominal Value	Unit
Durometer Hardness (10 sec)	88	
Mechanical	Nominal Value	Unit
Tensile Strength	16.5	MPa
Tensile Elongation (Break)	300	%
Thermal	Nominal Value	Unit
Brittleness Temperature	-37.0	°C
Additional Information	Nominal Value	Unit
Limited Oxygen Index	33	%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT