INLUBE PCCF10TF15

Polycarbonate

General Information

Infinity LTL Engineered Compounds

Message:

Inlube PTFE, silicone, MoS2 and graphite internally lubricated compounds

Offered in all Infinity base resins and can be combined with reinforcements and process additives

Provide reduced coefficient of friction and low wear, including enhanced mechanical and thermal propertie

| Filler / Reinforcement | Carbon Fiber,10% Filler by Weight | | | |
|--|-----------------------------------|----------|-------------|--|
| Additive | PTFE Lubricant (15%) | | | |
| Features | Good Wear Resistance | | | |
| | Low Friction | | | |
| | Lubricated | | | |
| | | | | |
| Physical | Nominal Value | Unit | Test Method | |
| Specific Gravity | 1.33 | g/cm³ | ASTM D792 | |
| Specific Volume | 0.753 | cm³/g | | |
| Molding Shrinkage - Flow | 0.20 to 0.30 | % | ASTM D955 | |
| Water Absorption (24 hr) | 0.080 | % | ASTM D570 | |
| Hardness | Nominal Value | Unit | Test Method | |
| Rockwell Hardness (M-Scale) | 82 | | ASTM D785 | |
| Mechanical | Nominal Value | Unit | Test Method | |
| Tensile Strength (Yield) | 107 | МРа | ASTM D638 | |
| Flexural Modulus | 6210 | МРа | ASTM D790 | |
| Flexural Strength | 145 | МРа | ASTM D790 | |
| Impact | Nominal Value | Unit | Test Method | |
| Notched Izod Impact (3.18 mm) | 59 | J/m | ASTM D256 | |
| Unnotched Izod Impact (3.18 mm) | 800 | J/m | ASTM D256 | |
| Thermal | Nominal Value | Unit | Test Method | |
| Deflection Temperature Under Load (1.8 | | | | |
| MPa, Unannealed) | 143 | °C | ASTM D648 | |
| CLTE - Flow | 2.7E-5 | cm/cm/°C | ASTM D696 | |
| Electrical | Nominal Value | Unit | Test Method | |
| Surface Resistivity | 1.0E+2 to 1.0E+6 | ohms | ASTM D257 | |
| Flammability | Nominal Value | Unit | Test Method | |
| Flame Rating (1.59 mm) | НВ | | UL 94 | |
| Injection | Nominal Value | Unit | | |
| Drying Temperature | 121 | °C | | |
| Drying Time | 4.0 | hr | | |

| Processing (Melt) Temp | 282 to 332 | °C | |
|------------------------|----------------|-----|--|
| Mold Temperature | 93.3 | °C | |
| Back Pressure | 0.345 to 0.689 | МРа | |
| Screw Speed | 40 to 70 | rpm | |
| Vent Depth | 0.038 to 0.076 | mm | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

