

# SABIC® PPcompound 2500-6

Polypropylene

Saudi Basic Industries Corporation (SABIC)

## Message:

SABIC® PPcompound 2500/6 is a mineral filled modified polypropylene. Typical material properties include very high flow, high impact, good stiffness and low shrinkage and CLTE. Typical material properties also include good chemical resistance and esthetical performance. Typical applications include automotive exterior trims such as lateral siding, bumper strips and bumpers. It can be used in painted and unpainted applications with UV stabilization added on demand.

SABIC® PPcompound 2500/6 is a designated automotive grade.

General Information			
Filler / Reinforcement	Mineral		
Additive	Impact Modifier		
Features	Good Chemical Resistance		
	Good Stiffness		
	High Flow		
	High Impact Resistance		
	Impact Modified		
	Low CLTE		
	Low Shrinkage		
	Paintable		
Uses	Automotive Applications		
	Automotive Bumper		
	Automotive Exterior Trim		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.960	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	30	g/10 min	ISO 1133
Molding Shrinkage (24 hr)	0.80	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2/5/50
Yield, 3.20 mm, Injection Molded	19.0	MPa	
Break, 3.20 mm, Injection Molded	15.0	MPa	
Tensile Strain (Break, 3.20 mm, Injection Molded)	> 400	%	ISO 527-2/5/50
Flexural Modulus <sup>1</sup> (Injection Molded)	1100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method

Charpy Notched Impact Strength (23°C, Injection Molded)	No Break		ISO 179/1eA
Charpy Unnotched Impact Strength (-40°C, Injection Molded)	No Break		ISO 179/1eU
Notched Izod Impact Strength			ISO 180/4A
-20°C, Injection Molded	15	kJ/m <sup>2</sup>	
0°C, Injection Molded	No Break		
23°C, Injection Molded	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	90.0	°C	ISO 75-2/B
Vicat Softening Temperature	125	°C	ISO 306/A
CLTE - Flow			ASTM D696
-30 to 30°C	6.0E-5	cm/cm/°C	
23 to 80°C	9.0E-5	cm/cm/°C	
NOTE			
1.	Method I (3 point load)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

