Sumiliteresin® PR-53497

Phenolic

SBHPP

Message:

SUMILITERESIN® PR-53497 is a Powder novolac resin based on Phenolic Novolac polymer. It is supplied in the form of Powder for Friction Materials.

General Information			
Forms	Powder		
Physical	Nominal Value	Unit	
Flow Length (125°C)	2.70	cm	
Thermal	Nominal Value	Unit	
Melting Temperature	98.0	°C	
Uncured Properties	Nominal Value	Unit	
Gel Time (150°C)	0.75	min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

