

# Moplen D50G

Polypropylene Homopolymer  
Shazand (Arak) Petrochemical Corporation

Message:

Moplen D50G is a homo-polymer with a high molecular weight and outstanding mechanical properties. The product shows excellent process ability in extrusion applications and exhibits excellent long-term heat aging resistance.

Moplen D50G is well suited for technical extrusion applications that require both high stiffness and high impact resistance.

Typical applications include the extrusion of thick, heavy sheet for industrial applications, strapping, tubes, profiles and pipes.

Moplen D50G is also used for the extrusion of thin sheet for thermoforming dairy tubs and other food packaging.

Extrusion blow moulded small containers and technical parts are other typical applications of Moplen D50G.

Moplen D50G is also appropriate for injection moulding wheels, fittings and high performance industrial components.

\* Moplen D50G is suitable for food contact.

General Information			
Features	Food Contact Acceptable		
	Good Heat Aging Resistance		
	Good Processability		
	High Impact Resistance		
	High Molecular Weight		
	High Stiffness		
	Homopolymer		
Uses	Blown Containers		
	Engineering Parts		
	Fittings		
	Food Containers		
	Food Packaging		
	Industrial Applications		
	Piping		
	Profiles		
	Sheet		
	Strapping		
	Tubing		
	Wheels		
Processing Method	Casting		
	Extrusion		
	Extrusion Blow Molding		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	0.30	g/10 min	ASTM D1238

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	82		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	33.0	MPa	ASTM D638
Tensile Elongation (Yield)	13	%	ASTM D638
Flexural Modulus	1400	MPa	ASTM D790
Aging	Nominal Value	Unit	Test Method
Oven Aging (150°C)	2.1	month	ASTM D3012
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	90.0	°C	ASTM D648
Vicat Softening Temperature	152	°C	ASTM D1525 <sup>1</sup>
NOTE			
1.	Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT