

Polimid B AV Y

Polyamide 6

Poliblend S.p.a.

Message:

Polimid B AV Y is a Polyamide 6 (Nylon 6) material. It is available in Africa & Middle East, Asia Pacific, Europe, or Latin America.

Important attributes of Polimid B AV Y are:

Flame Rated

Lubricated

General Information			
Additive	Molybdenum Disulfide Lubricant		
Features	Lubricated		
Appearance	Natural Color		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Molding Shrinkage	1.0 to 1.4	%	
Water Absorption (23°C, 24 hr)	2.0	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3000	MPa	ISO 527-2
Tensile Stress (Yield)	85.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	5.0	%	
Break	85	%	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	5.5	kJ/m ²	ISO 180/A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	180	°C	ISO 75-2/B
1.8 MPa, Unannealed	80.0	°C	ISO 75-2/A
Continuous Use Temperature ¹	80.0	°C	
Vicat Softening Temperature	206	°C	ISO 306/A120
Ball Pressure Test (165°C)	Pass		IEC 60695-10-2
Melting Temperature	222	°C	DSC
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	> 600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	HB		
1.60 mm	HB		
3.20 mm	HB		
Injection	Nominal Value	Unit	

Drying Temperature	90.0 to 100	°C
Drying Time	> 3.0	hr
Processing (Melt) Temp	230 to 250	°C
Mold Temperature	70.0 to 80.0	°C

NOTE

1.
- Without Load

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT