

KumhoSunny PA/PPE HAP8940

Polyamide + PPE

Shanghai KumhoSunny Plastics Co., Ltd.

Message:

HAP8940 is an unreinforced PA66/PPE alloy, with excellent chemical resistance, paintability and high impact.

General Information			
Features	Good Chemical Resistance		
	Good Impact Resistance		
	Paintable		
UL File Number	E254819		
	E65424		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.09	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (280°C/5.0 kg)	30	g/10 min	ISO 1133
Molding Shrinkage (23°C)	1.1 to 1.5	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	62.0	MPa	ISO 527-2/50
Tensile Strain (Break)	80	%	ISO 527-2/50
Flexural Modulus ¹ (64.0 mm)	2190	MPa	ISO 178
Flexural Stress ² (64.0 mm)	72.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ³			ISO 179
-30°C	41	kJ/m ²	
23°C	13	kJ/m ²	
Charpy Unnotched Impact Strength ⁴			ISO 179
-30°C	No Break		
23°C	No Break		
Notched Izod Impact Strength ⁵			ISO 180
-30°C	13	kJ/m ²	
23°C	37	kJ/m ²	
Unnotched Izod Impact Strength ⁶			ISO 180
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁷			

0.45 MPa, Unannealed	175	°C	ISO 75-2/B
1.8 MPa, Unannealed	110	°C	ISO 75-2/A
Vicat Softening Temperature	190	°C	ISO 306/B50
CLTE			ISO 11359-2
Flow : -40 to 40°C	9.0E-5	cm/cm/°C	
Transverse : -40 to 40°C	1.3E-5	cm/cm/°C	

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms·cm	IEC 60093

NOTE

- | | |
|----|------------------|
| 1. | 2.0 mm/min |
| 2. | 2.0 mm/min |
| 3. | Condition: 4 J |
| 4. | Condition: 4 J |
| 5. | Condition: 5.5 J |
| 6. | Condition: 5.5 J |
| 7. | 120°C/h |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT