

SPESIN® KP210

Polybutylene Terephthalate

Kolon Plastics, Inc.

Message:

SPESIN® KP210 is a polybutene terephthalate (PBT) product. It can be processed by extrusion and is available in North America, Latin America, Europe or Asia Pacific.

- Features include:
- flame retardant/rated flame
 - ROHS certification

General Information			
RoHS Compliance	RoHS compliance		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.7 - 2.3	%	ASTM D955
Water Absorption (Equilibrium, 23°C, 60% RH)	0.080	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	78		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	58.8	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	100	%	ASTM D638
Flexural Modulus (23°C)	2060	MPa	ASTM D790
Flexural Strength (23°C)	88.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	39	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	155	°C	ASTM D648
1.8 MPa, not annealed	60.0	°C	ASTM D648
Peak Melting Temperature	224	°C	ASTM D3418
CLTE - Flow	8.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	28	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.10		ASTM D150
Arc Resistance	120	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT