

DURACON® AW-09

Acetal (POM) Copolymer + PE

Polyplastics Co., Ltd.

Message:

High Sliding, Special Lubricant, High Viscosity

General Information			
Additive	Lubricant		
Features	Low friction coefficient		
	Lubrication		
	Viscosity, High		
Forms	Particle		
Processing Method	Injection molding		
Part Marking Code (ISO 11469)	>POM+PE		
Physical	Nominal Value	Unit	Test Method
Density	1.37	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.0	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	2.50	cm ³ /10min	ISO 1133
Water Absorption (23°C, 24 hr)	0.70	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	70		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2200	MPa	ISO 527-2
Tensile Stress	54.0	MPa	ISO 527-2
Nominal Tensile Strain at Break	30	%	ISO 527-2
Flexural Modulus	2050	MPa	ISO 178
Flexural Stress	70.0	MPa	ISO 178
Coefficient of friction-Dynamic			JIS K7218
-- 1	0.300		JIS K7218
-- 2	0.160		JIS K7218
Color Number	CF2001		
Specific Wear			JIS K7218
-- 3		10 ⁻³ mm ³ /N·km	JIS K7218
-- 4	14.0	10 ⁻³ mm ³ /N·km	JIS K7218
-- 5	7.00	10 ⁻³ mm ³ /N·km	JIS K7218
-- 6	0.200	10 ⁻³ mm ³ /N·km	JIS K7218
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	8.0	kJ/m ²	ISO 179/1eA

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	70.0	°C	ISO 75-2/A
Linear thermal expansion coefficient			Internal method
Flow: 23 to 55°C	1.3E-4	cm/cm/°C	Internal method
Lateral: 23 to 55°C	1.3E-4	cm/cm/°C	Internal method

Injection	Nominal Value	Unit
Drying Temperature	80.0 - 90.0	°C
Drying Time	3.0 - 4.0	hr
Processing (Melt) Temp	190 - 210	°C
Mold Temperature	60.0 - 80.0	°C
Injection Pressure	49.0 - 98.0	MPa
Screw Speed	100 - 150	rpm

Injection instructions

Injection Speed: 5-50mm/s (0.3-3m/min)Molding Cycle:
Injection Holding Pressure: Gate sealing time + alpha
Cooling: Plasticizing time or ejection capable time

NOTE

1. vs M90-44, pressure 0.06MPa, 15cm/s
2. vs C-Steel, pressure 0.98MPa, 30cm/s
3. vs C-Steel, steel side, pressure 0.98MPa, 30cm/s
4. vs M90-44, M90-44 side, pressure 0.06MPa, 15cm/s
5. vs M90-44, material side, pressure 0.06MPa, 15cm/s
6. vs C-Steel, material side, pressure 0.98MPa, 30cm/s

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT