

Jiangsu Meilan XXMLF2-13

Fluoroelastomer

Jiangsu Meilan Chemical Co., Ltd.

Message:

Fluoroelastomer (F26) (FKM)

Quality Standard: Q/321200GDH010—2010

General Information		
Appearance	Transparent - Slight Yellow White	
Physical	Nominal Value	Unit
Specific Gravity	1.80 to 1.84	g/cm ³
Mooney Viscosity (ML 1+10, 121°C)	51 to 90	MU
Moisture Content	< 0.050	%
Oil Resistance - 1# jet fuel oil, 200°C/24h	< 6.0	%
Elastomers	Nominal Value	Unit
Tensile Strength	> 9.00	MPa
Tensile Elongation (Break)	> 160	%
Compression Set ¹ (200°C, 70 hr)	< 30	%
NOTE		

1. Bisphenol-AF vulcanization system

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

