

Vyncolit® X682

Phenolic

Vyncolit N.V.

Message:

Vyncolit X682 is a glass fiber filled phenolic molding compound, with excellent mechanical properties. It is graphite modified to improve the friction properties.

General Information	
Filler / Reinforcement	Glass fiber reinforced material
Additive	Graphite powder lubricant
Features	Lubrication
Appearance	Black
Forms	Particle
Processing Method	Resin transfer molding
	Compression molding
	Injection molding

Physical	Nominal Value	Unit	Test Method
Density	1.70	g/cm ³	ISO 1183
Molding Shrinkage - Flow	0.20 - 0.30	%	ISO 294-4
Water Absorption (23°C, 24 hr)	0.15	%	ISO 62

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (Injection Molded)	13500	MPa	ISO 527-2
Tensile Stress (Break, Injection Molded)	75.0	MPa	ISO 527-2
Tensile Strain (Break, Injection Molded)	0.65	%	ISO 527-2
Flexural Modulus (Injection Molded)	13000	MPa	ISO 178
Flexural Stress (Injection Molded)	170	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (Injection Molded)	3.3	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	10	kJ/m ²	ISO 179

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
1.8 MPa, not annealed	175	°C	ISO 75-2/A
8.0 MPa, not annealed	160	°C	ISO 75-2/C
Linear thermal expansion coefficient			ASTM E831
Flow	2.5E-5	cm/cm/°C	ASTM E831
Lateral	4.5E-5	cm/cm/°C	ASTM E831

Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	125	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method

Flame Rating		UL 94
1.60 mm	V-1	UL 94
4.00 mm	V-0	UL 94
Injection	Nominal Value	Unit
Rear Temperature	60.0	°C
Middle Temperature	73.9	°C
Nozzle Temperature	87.8	°C
Processing (Melt) Temp	98.9 - 116	°C
Mold Temperature	166 - 188	°C
Injection Pressure	100 - 248	MPa
Holding Pressure	30.0 - 89.6	MPa
Back Pressure	4.83 - 15.2	MPa
Injection instructions		

Plastication: 50rpm Injection Time: 2 to 8 sec Hold Time: 1 to 5 sec/mm Cure Time, 0.125 in: 5 to 12 sec/mm All ISO properties listed were tested in accordance with ISO 3167 The value listed as Molding Shrinkage, ISO 294-4, was tested in accordance with ISO 2577. ISO Type: PF 2 C1 Powder Density, ISO 60: 0.7 to 0.85 g/cm³ Post Shrinkage, ISO 2577: 0.05 to 0.15% HDT A (1.80 MPa) Unannealed, ISO 75A, Injection Molding: 170 to 180°C CHDT A (8.0 MPa) Unannealed, ISO 75A, Injection Molding: 150 to 170°C CCLTE, Flow (TMA), ASTM E831, Injection Molding: 20 to 30 cm⁻⁶/cm°C CCLTE, Transverse (TMA), ASTM E831, Injection Molding: 40 to 50 cm⁻⁶/cm°C Flexural Strength, ISO 178, Injection Molding: 160 to 180 MPa Flexural Modulus, ISO 178, Injection Molding: 12 to 14 GPa Strain to failure in Flexure, ISO 178, Injection Molding: 1.3 to 1.4% Tensile Stress at Break, ISO 527-1,-2, Injection Molding: 70 to 80 MPa Tensile Modulus, ISO 527-1,-2, Injection Molding: 12.5 to 14.5 GPa Tensile Strain at Break, ISO 527-1,-2, Injection Molding: 0.6 to 0.7% Charpy Notched Impact Strength, ISO 179, Injection Molding: 2.5 to 4 kJ/m² Charpy Unnotched Impact Strength, ISO 179, Injection Molding: 9 to 11 kJ/m² Compressive Strength, ISO 604: 250 to 280 MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT