

Dynacom 401-G35

Polyamide 6

Dynachem Co. Ltd.

Message:

Dynacom 401-G35 is a Polyamide 6 (Nylon 6) material. It is available in Asia Pacific.

General Information				
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.40	--	g/cm ³	ASTM D792
Molding Shrinkage - Flow ¹	0.20 to 0.80	--	%	ASTM D955
Water Absorption (23°C, 24 hr)	1.0	--	%	ASTM D570
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (R-Scale)	121	--		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength ²	176	108	MPa	ASTM D638
Tensile Elongation ³ (Break)	5.0	5.0	%	ASTM D638
Flexural Modulus ⁴	8820	5290	MPa	ASTM D790
Flexural Strength ⁵	255	147	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	130	200	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	210	--	°C	ASTM D648
Vicat Softening Temperature	225	--	°C	ASTM D1525 ⁶
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+15	1.0E+12	ohms·cm	ASTM D257
Dielectric Strength (1.00 mm)	19	15	kV/mm	ASTM D149
Arc Resistance	105	120	sec	ASTM D495
Additional Information	Dry	Conditioned	Unit	
Conditioned Moisture Content	--	2.5	%	
NOTE				
1.	Thickness: 2 to 3 mm			
2.	5.0 mm/min			
3.	5.0 mm/min			
4.	3.0 mm/min			
5.	3.0 mm/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

