

Arnite® T06 202 XL

Polybutylene Terephthalate

DSM Engineering Plastics

Message:

Arnite® T06 202 XL is a Polybutylene Terephthalate (PBT) material. It is available in Europe for injection molding.

Important attributes of Arnite® T06 202 XL are:

Flame Rated

Medium Viscosity

General Information			
Features	Low to No Outgassing		
	Medium Viscosity		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.30	g/cm ³	ISO 1183
Water Absorption			ISO 62
Saturation, 23°C	0.45	%	
Equilibrium, 23°C, 50% RH	0.18	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2700	MPa	ISO 527-2
Tensile Stress (Yield)	58.0	MPa	ISO 527-2
Tensile Strain (Yield)	4.0	%	ISO 527-2
Nominal Tensile Strain at Break	50	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	5.0	kJ/m ²	
23°C	5.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	170	°C	ISO 75-2/B
1.8 MPa, Unannealed	60.0	°C	ISO 75-2/A
Melting Temperature ¹	225	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow	9.0E-5	cm/cm/°C	
Transverse	9.0E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method

Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Electric Strength	27	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	3.50		
1 MHz	3.20		
Dissipation Factor			IEC 60250
100 Hz	2.0E-3		
1 MHz	0.020		
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flammability Classification			IEC 60695-11-10, -20
0.750 mm	HB		
1.50 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	100 to 120	°C	
Drying Time	3.0 to 12	hr	
Rear Temperature	230 to 240	°C	
Middle Temperature	230 to 250	°C	
Front Temperature	240 to 260	°C	
Nozzle Temperature	240 to 260	°C	
Processing (Melt) Temp	240 to 270	°C	
Mold Temperature	60.0 to 100	°C	
Injection Rate	Moderate-Fast		
Back Pressure	3.00 to 10.0	MPa	
Screw Compression Ratio	2.5:1.0		
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT