

LNP™ LUBRICOMP™ RP004 compound

Polyamide 66

SABIC Innovative Plastics

Message:

LNP LUBRICOMP* RP004 is a compound based on Nylon 66 resin containing 20% PTFE/Silicone. Added features of this material include: Wear Resistant.

Also known as: LNP* LUBRICOMP* Compound RL-4540

Product reorder name: RP004

General Information			
UL YellowCard	E121562-101344545		
Additive	PTFE + Silicone Lubricant (20%)		
Features	Good Wear Resistance		
	Lubricated		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			ASTM D955
Flow : 24 hr	1.0 to 3.0	%	
Across Flow : 24 hr	1.0 to 3.0	%	
Water Absorption			
24 hr, 50% RH	0.84	%	ASTM D570
Equilibrium, 23°C, 50% RH	1.1	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2620	MPa	ASTM D638
--	2730	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	61.0	MPa	ASTM D638
Yield	63.0	MPa	ISO 527-2/5
Break ³	61.0	MPa	ASTM D638
Break	63.0	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁴	22	%	ASTM D638
Yield	26	%	ISO 527-2/5
Break ⁵	23	%	ASTM D638
Break	27	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁶	2260	MPa	ASTM D790
-- ⁷	2400	MPa	ISO 178
Coefficient of Friction			ASTM D3702 Modified

vs. Itself - Dynamic	0.020		
vs. Itself - Static	0.045		
Wear Factor - Washer	3.50	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	53	J/m	ASTM D256
23°C ⁸	5.2	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	350	J/m	ASTM D4812
23°C ⁹	88	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Total Energy	6.70	J	ASTM D3763
--	1.20	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	237	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ¹⁰	200	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	64.0	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ¹¹	63.0	°C	ISO 75-2/Af
CLTE			ASTM D696
Flow : -30 to 30°C	8.4E-5	cm/cm/°C	
Transverse : -30 to 30°C	9.4E-5	cm/cm/°C	
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 to 0.25	%	
Rear Temperature	266 to 277	°C	
Middle Temperature	282 to 293	°C	
Front Temperature	293 to 304	°C	
Processing (Melt) Temp	277 to 288	°C	
Mold Temperature	82.2 to 93.3	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	Type I, 5.0 mm/min		
3.	Type I, 5.0 mm/min		
4.	Type I, 5.0 mm/min		
5.	Type I, 5.0 mm/min		
6.	1.3 mm/min		
7.	2.0 mm/min		
8.	80*10*4		

9.	80*10*4
10.	80*10*4 mm
11.	80*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

