# Verolloy S3100

### Polycarbonate + ABS

PlastxWorld Inc.

#### Message:

Verolloy S3100 is a Polycarbonate + ABS (PC+ABS) product. It can be processed by injection molding and is available in Europe or North America. Characteristics include: Flame Rated Flame Retardant

General Information UL YellowCard E315545-100091182 Features Flame Retardant **General Purpose** Uses **General Purpose** Forms Pellets Processing Method Injection Molding Physical Nominal Value Unit Test Method Specific Gravity 1.23 g/cm<sup>3</sup> ASTM D792 Melt Mass-Flow Rate (MFR) (240°C/5.0 kg) 8.0 g/10 min **ASTM D1238** Molding Shrinkage - Flow 0.40 to 0.60 ASTM D955 % Mechanical Nominal Value Unit Test Method Tensile Strength (Yield) 50.3 MPa ASTM D638 100 Tensile Elongation (Break) % ASTM D638 Flexural Modulus 2060 MPa ASTM D790 Flexural Strength 74.5 ASTM D790 MPa Impact Nominal Value Unit Test Method Notched Izod Impact (23°C, 3.18 mm) 480 J/m ASTM D256 Thermal Nominal Value Unit Test Method Deflection Temperature Under Load (1.8 109 °C ASTM D648 MPa, Unannealed) Nominal Value Flammability Test Method Flame Rating (1.60 mm) V-0 UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

