

# Nordbak Cold Cure Backing

Epoxy; Epoxide

Loctite®

## Message:

Nordbak Cold Cure Backing is an Epoxy; Epoxide (Epoxy) product. It is available in North America. Primary characteristic: flame retardant.

General Information			
Features	Flame Retardant		
	Good Stability		
Uses	Machinery Maintenance/Repair		
	Metal Replacement		
Forms	Pellets		
Hardness	Nominal Value		Test Method
Durometer Hardness (Shore D)	90		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	37.9	MPa	ASTM D638
Compressive Strength	109	MPa	ASTM D695
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	76.7	°C	ASTM D794
Thermoset	Nominal Value	Unit	
Pot Life (10°C)	8.0 to 11	min	
Demold Time (10°C)	240	min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT