TECHNOGRAN® PEHDI SUV

High Density Polyethylene

Eurocompound Polymers

Message:

TECHNOGRAN® PEHDI SUV is a High Density Polyethylene material. It is available in Europe for injection molding. Important attributes of TECHNOGRAN® PEHDI SUV are: Good UV Resistance UV Stabilized

General Information			
Additive	UV Stabilizer		
Features	Good UV Resistance		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.900 to 0.980	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16			
kg)	2.5 to 6.5	g/10 min	ISO 1133
Water Absorption (23°C, 24 hr)	< 0.20	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	750 to 1350	MPa	ISO 527-2
Tensile Stress (Yield)	16.0 to 26.0	MPa	100 505 0
	10.0 10 20.0	MPa	ISO 527-2
Tensile Strain (Break)	> 500	%	ISO 527-2 ISO 527-2
Tensile Strain (Break) Flexural Modulus		-	
	> 500	%	ISO 527-2
Flexural Modulus	> 500 700 to 760	% MPa	ISO 527-2 ISO 178
Flexural Modulus Flexural Stress	> 500 700 to 760 9.00 to 19.0	% MPa MPa	ISO 527-2 ISO 178 ISO 178

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

