

Adell Polyamide AR-37 (P)

Polyamide 66

Adell Plastics, Inc.

Message:

Adell Polyamide AR-37 (P) is a Polyamide 66 (Nylon 66) material filled with 33% glass fiber. It is available in North America.

General Information			
Filler / Reinforcement	Glass Fiber,33% Filler by Weight		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.36	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20 to 0.50	%	ASTM D955
Water Absorption (24 hr)	0.70	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	101		
R-Scale	123		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	214	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	9650	MPa	ASTM D790
Flexural Strength (Yield)	283	MPa	ASTM D790
Compressive Strength	245	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	120	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	249	°C	
1.8 MPa, Unannealed	249	°C	
Melting Temperature	254 to 271	°C	
CLTE - Flow	2.3E-5	cm/cm/°C	ASTM D696
Thermal Conductivity	0.50	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength	21	kV/mm	ASTM D149

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

