

SD POLYCA™ LR8081W

Polycarbonate

Sumika Styron Polycarbonate Limited

Message:

Our light reflective products have high light reflectivity and good ignition resistant property, based on our excellent compounding technology. These grades are used for light reflective parts in LCD displays.

General Information			
UL YellowCard	E123529-100368665		
Additive	Flame retardancy		
Features	High reflectivity		
	Flame retardant		
	Flame retardancy		
Uses	LCD application		
	Electrical housing		
	Sheet		
Part Marking Code	>PC FR(76)		
Physical	Nominal Value	Unit	Test Method
Density	1.31	g/cm ³	ISO 1183
Molding Shrinkage			ASTM D955
Flow	0.50 - 0.70	%	ASTM D955
Transverse flow	0.50 - 0.70	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.17	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	55.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	30	%	ASTM D638, ISO 527-2
Flexural Modulus			
--	2400	MPa	ASTM D790
--	2500	MPa	ISO 178
Flexural Strength	87.0	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	20	kJ/m ²	ISO 179
Notched Izod Impact (23°C)	290	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, not annealed	127	°C	ASTM D648
1.8 MPa, not annealed	120	°C	ISO 75-2/A
Flammability	Nominal Value		Test Method

Flame Rating (1.5 mm)	V-0	UL 94
Optical	Nominal Value	Test Method
Refractive Index ¹	95.00	Internal method
NOTE		
1.	Thickness: 1 mm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT