

LEXAN™ 505R resin

Polycarbonate

SABIC Innovative Plastics

Message:

LEXAN 505R Polycarbonate (PC) resin is a 10% glass fiber filled, injection moldable grade. LEXAN 505R contains non-chlorinated, non-brominated flame retardant systems with UL-94 V0 rating at 1.5mm. It is available in various opaque color options for high stiffness applications.

General Information			
UL YellowCard	E45329-302575		
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
Additive	Flame retardancy		
Features	Chlorine Free		
	Rigidity, high		
	Bromine-free		
	Flame retardancy		
RoHS Compliance	RoHS compliance		
Appearance	Opacity		
	Available colors		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.26	g/cm ³	ASTM D792
--	1.25	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	7.0	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	7.00	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow			Internal method
-- ¹	0.20 - 0.60	%	Internal method
3.20 mm	0.50 - 0.70	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.31	%	ISO 62
Equilibrium, 23°C, 50% RH	0.13	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	115	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ²	3930	MPa	ASTM D638
--	3300	MPa	ISO 527-2/1
Tensile Strength			

Yield ³	63.0	MPa	ASTM D638
Yield	60.0	MPa	ISO 527-2/5
Fracture ⁴	48.0	MPa	ASTM D638
Fracture	45.0	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁵	3.0	%	ASTM D638
Yield	5.0	%	ISO 527-2/5
Fracture ⁶	12	%	ASTM D638
Fracture	7.0	%	ISO 527-2/5
Flexural Modulus			
50.0mm span ⁷	3530	MPa	ASTM D790
-- ⁸	3400	MPa	ISO 178
Flexural Stress			
--	95.0	MPa	ISO 178
Fracture, 50.0mm span ⁹	108	MPa	ASTM D790
Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-17 Wheel)	11.0	mg	Internal method
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			
-30°C ¹⁰	9.0	kJ/m ²	ISO 179/1eA
23°C ¹¹	9.0	kJ/m ²	ISO 179/1eA
23°C ¹²	10	kJ/m ²	ISO 179/1eA
23°C	15	kJ/m ²	ISO 179/2C
Charpy Unnotched Impact Strength ¹³			ISO 179/1eU
-30°C	No Break		ISO 179/1eU
23°C	No Break		ISO 179/1eU
Notched Izod Impact			
-30°C	80	J/m	ASTM D256
23°C	110	J/m	ASTM D256
-30°C ¹⁴	8.0	kJ/m ²	ISO 180/1A
23°C ¹⁵	10	kJ/m ²	ISO 180/1A
23°C ¹⁶	8.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	1600	J/m	ASTM D4812
-30°C ¹⁷	No Break		ISO 180/1U
-30°C ¹⁸	130	kJ/m ²	ISO 180/1U
23°C ¹⁹	No Break		ISO 180/1U
Instrumented Dart Impact (23°C, Total Energy)	61.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	143	°C	ASTM D648
0.45 MPa, unannealed, 100 mm span ²⁰	144	°C	ISO 75-2/Be

1.8 MPa, unannealed, 3.20mm	138	°C	ASTM D648
1.8 MPa, unannealed, 100 mm span ²¹	136	°C	ISO 75-2/Ae
1.8 MPa, annealed ²²	136	°C	ISO 75-2/Ae
Vicat Softening Temperature			
--	149	°C	ASTM D1525 ²³
--	141	°C	ISO 306/B50
--	143	°C	ISO 306/B120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
Linear thermal expansion coefficient			
Flow: -40 to 40°C	4.7E-5	cm/cm/°C	ASTM E831
Flow: 23 to 80°C	4.0E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	8.5E-5	cm/cm/°C	ASTM E831
Lateral: 23 to 80°C	7.0E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.21	W/m/K	ISO 8302
RTI Elec	130	°C	UL 746
RTI Imp	130	°C	UL 746
RTI	130	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Dielectric Strength			IEC 60243-1
0.800mm, in oil	33	kV/mm	IEC 60243-1
1.60mm, in oil	25	kV/mm	IEC 60243-1
3.20mm, in oil	16	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
50 Hz	2.90		IEC 60250
60 Hz	2.90		IEC 60250
1 MHz	2.80		IEC 60250
Dissipation Factor			IEC 60250
50 Hz	1.0E-3		IEC 60250
60 Hz	1.0E-3		IEC 60250
1 MHz	0.010		IEC 60250
Comparative Tracking Index	150	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	V-0		UL 94
2.00 mm, Testing by SABIC	5VB		UL 94
3.00 mm	5VA		UL 94
Glow Wire Flammability Index (1.00 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (1.00 mm)	825	°C	IEC 60695-2-13
Oxygen Index	37	%	ISO 4589-2
Injection	Nominal Value	Unit	

Drying Temperature	120	°C
Drying Time	2.0 - 4.0	hr
Suggested Max Moisture	0.020	%
Hopper Temperature	60.0 - 80.0	°C
Rear Temperature	270 - 300	°C
Middle Temperature	280 - 310	°C
Front Temperature	290 - 320	°C
Nozzle Temperature	280 - 310	°C
Processing (Melt) Temp	290 - 320	°C
Mold Temperature	80.0 - 120	°C

NOTE		
1.	Tensile Bar	
2.	5.0 mm/min	
3.	Type 1, 5.0 mm/min	
4.	Type 1, 5.0 mm/min	
5.	Type 1, 5.0 mm/min	
6.	Type 1, 5.0 mm/min	
7.	1.3 mm/min	
8.	2.0 mm/min	
9.	1.3 mm/min	
10.	80*10*3 sp=62mm	
11.	80*10*4 sp=62mm	
12.	80*10*3 sp=62mm	
13.	80*10*4 sp=62mm	
14.	80*10*4	
15.	80*10*3	
16.	80*10*4	
17.	80*10*4	
18.	80*10*3	
19.	80*10*3	
20.	120*10*4 mm	
21.	120*10*4 mm	
22.	2 hr, 120°C	
23.	标准 B (120°C/h), 载荷2 (50N)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

