

Tenac™-C 8520

Acetal (POM) Copolymer
Asahi Kasei Chemicals Corporation

Message:

Tenac™-C 8520 is an Acetal (POM) Copolymer product. It is available in Africa & Middle East, Asia Pacific, Europe, or North America. Applications of Tenac™-C 8520 include engineering/industrial parts and housings.

Characteristics include:

- Flame Rated
- Copolymer
- High Flow
- Low Viscosity

General Information	
UL YellowCard	E48285-240795
Features	Copolymer
	High Flow
	Low Viscosity
Uses	Engineering Parts
	Gears
	Housings

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	45	g/10 min	ISO 1133
Molding Shrinkage - Flow	1.6 to 2.0	%	Internal Method
Water Absorption (23°C, 24 hr, 50% RH)	0.20	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	80		
R-Scale	115		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2850	MPa	ISO 527-2
Tensile Stress			
Yield	65.0	MPa	ISO 527-2
--	64.0	MPa	ASTM D638
Tensile Elongation			
Break	28	%	ASTM D638
Break	25	%	ISO 527-2
Flexural Modulus			
--	2680	MPa	ASTM D790

--	2700	MPa	ISO 178
Flexural Strength	95.0	MPa	ASTM D790
Taber Abrasion Resistance	14.0	mg	ASTM D1044
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	4.5	kJ/m ²	ISO 179
Notched Izod Impact	50	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	158	°C	ASTM D648
0.45 MPa, Unannealed	156	°C	ISO 75-2/B
1.8 MPa, Unannealed	110	°C	ASTM D648
1.8 MPa, Unannealed	100	°C	ISO 75-2/A
CLTE - Flow	1.0E-4	cm/cm/°C	ASTM D696, ISO 11359-2
Specific Heat	1470	J/kg/°C	
Thermal Conductivity	0.23	W/m/K	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16 to 1.0E+17	ohms	ASTM D257
Volume Resistivity (23°C)	1.0E+15 to 1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	19	kV/mm	ASTM D149
Dielectric Constant (23°C, 1 MHz)	3.90		ASTM D150
Dissipation Factor (23°C, 1 MHz)	8.0E-3		ASTM D150
Arc Resistance	250	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.750 mm)	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT