

Leona™ 14G15

Polyamide 66

Asahi Kasei Chemicals Corporation

Message:

Leona™ 14G15 is a Polyamide 66 (Nylon 66) product filled with 15% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, or North America. Applications of Leona™ 14G15 include automotive, electrical/electronic applications and engineering/industrial parts.

Characteristics include:

Flame Rated

Creep Resistant

Fatigue Resistant

Heat Resistant

Heat Stabilizer

General Information	
UL YellowCard	E48285-240895
Filler / Reinforcement	Glass Fiber, 15% Filler by Weight
Additive	Heat Stabilizer
Features	Fatigue Resistant
	Good Creep Resistance
	Heat Stabilized
	High Stiffness
	High Strength
	Medium Heat Resistance
Uses	Automotive Applications
	Automotive Under the Hood
	Electrical/Electronic Applications
	Structural Parts

Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.25	--	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage				Internal Method
Across Flow	1.2	--	%	
Flow	0.70	--	%	
Water Absorption				
Saturation, 23°C	--	2.1	%	
Equilibrium, 23°C, 50% RH	--	2.1	%	ISO 62
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness				ASTM D785, ISO 2039-2
M-Scale	94	71		
R-Scale	120	--		
Mechanical	Dry	Conditioned	Unit	Test Method

Tensile Modulus (23°C)	5800	3600	MPa	ISO 527-2
Tensile Stress				
Yield, 23°C	--	77.0	MPa	ISO 527-2
Break, 23°C	107	73.0	MPa	ISO 527-2
--	108	79.0	MPa	ASTM D638
Tensile Strain				
Yield, 23°C	--	6.0	%	ISO 527-2
Break	2.5	8.0	%	ASTM D638
Break, 23°C	2.5	11	%	ISO 527-2
Flexural Modulus				
--	4900	2500	MPa	ASTM D790
23°C	4800	3300	MPa	ISO 178
Flexural Strength				
--	167	108	MPa	ASTM D790
23°C	162	116	MPa	ISO 178
Taber Abrasion Resistance (1000 Cycles)	--	9.00	mg	ASTM D1044
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	6.0	5.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	26	38	kJ/m ²	ISO 179
Notched Izod Impact	49	59	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, Unannealed	258	--	°C	ASTM D648
0.45 MPa, Unannealed	260	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	240	--	°C	ASTM D648
1.8 MPa, Unannealed	235	--	°C	ISO 75-2/A
CLTE - Flow	4.0E-5	--	cm/cm/°C	ASTM D696
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+15	--	ohms	ASTM D257, IEC 60093
Volume Resistivity				
--	1.0E+15	--	ohms·cm	ASTM D257
23°C	1.0E+15	--	ohms·cm	IEC 60093
Dielectric Strength	26	--	kV/mm	ASTM D149, IEC 60243-1
Comparative Tracking Index (3.00 mm)	425	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.750 mm)	HB	--		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT