

# Mytex® AN16L(W)-44

Polypropylene

Mytex Polymers

## Message:

Compounded polypropylene produced for automotive exterior applications using Mytex® Technology.

General Information			
Uses	Automotive Exterior Parts		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.09	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	18	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	16.0	MPa	ISO 527-2/50
Flexural Modulus - Tangent <sup>1</sup>	1550	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	25	kJ/m <sup>2</sup>	ISO 180
NOTE			
1.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT