

Celanex® 3400-2

Polybutylene Terephthalate

Celanese Corporation

Message:

Celanex 3400-2 is a general purpose, 40% glass reinforced polybutylene terephthalate that offers a good combination of mechanical, electrical, and thermal properties. This grade provides outstanding processability and good chemical resistance. Celanex 3400 is a high flow material.

General Information			
UL YellowCard	E42337-234681	E45575-239395	
Filler / Reinforcement	Glass fiber reinforced material, 40% filler by weight		
Features	Workability, good		
	Good electrical performance		
	High liquidity		
	Good chemical resistance		
	General		
Uses	General		
RoHS Compliance	Contact manufacturer		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.61	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)	8.0	g/10 min	ASTM D1238
Molding Shrinkage			
Flow	0.30 - 0.50	%	ASTM D955
Vertical flow direction	0.70	%	ISO 294-4
Flow direction	0.30 - 0.50	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	0.12	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	93		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
23°C	11700	MPa	ASTM D638
--	12100	MPa	ISO 527-2/1A/1
Tensile Strength			
Fracture, 23°C	147	MPa	ASTM D638
Fracture	140	MPa	ISO 527-2/1A/5
Tensile Elongation			
Fracture, 23°C	2.0	%	ASTM D638
Fracture	2.4	%	ISO 527-2/1A/5
Flexural Modulus (23°C)	11000	MPa	ISO 178
Flexural Stress (23°C)	215	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	9.5	kJ/m ²	ISO 179/1eA
23°C	11	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	45	kJ/m ²	ISO 179/1eU
23°C	47	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C)	10	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	225	°C	ISO 75-2/B
0.45 MPa, annealed	223	°C	ASTM D648
1.8 MPa, not annealed	209	°C	ASTM D648
1.8 MPa, not annealed	212	°C	ISO 75-2/A
Glass Transition Temperature ¹	45.0	°C	ISO 11357-2
Melting Temperature ²	225	°C	ISO 11357-3, ASTM D3418
Linear thermal expansion coefficient			ISO 11359-2
Flow	1.5E-5	cm/cm/°C	ISO 11359-2
Lateral	1.0E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity			
--	1.0E+16	ohms · cm	ASTM D257
--	1.0E+15	ohms · cm	IEC 60093
Dielectric Strength			
-- ³	19	kV/mm	ASTM D149
--	19	kV/mm	IEC 60243-1
Dielectric Constant			
1 MHz	3.90		ASTM D150
100 Hz	3.50		IEC 60250
1 MHz	3.40		IEC 60250
Dissipation Factor			
1 MHz	2.0E-3		ASTM D150
1 MHz	0.013		IEC 60250
Arc Resistance	127	sec	ASTM D495
Comparative Tracking Index			
--	350	V	IEC 60112
--	500	V	ASTM D3638
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.710 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120 - 130	°C	

Drying Time	4.0	hr
Suggested Max Moisture	0.020	%
Suggested Max Regrind	25	%
Hopper Temperature	20.0 - 50.0	°C
Rear Temperature	230 - 240	°C
Middle Temperature	235 - 250	°C
Front Temperature	235 - 250	°C
Nozzle Temperature	240 - 260	°C
Processing (Melt) Temp	235 - 260	°C
Mold Temperature	65.0 - 96.0	°C
Injection Rate	Moderate-Fast	
Back Pressure	0.00 - 0.345	MPa

Injection instructions

Manifold Temperature: 250 to 260°C Zone 4 Temperature: 240 to 260°C Feed Temperature: 230 to 240°C

NOTE

1. 10°C/min
2. 10°C/min
3. Method A (short time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

