

AIE PBT 30G8F

Polybutylene Terephthalate
Asia International Enterprise (Hong Kong) Limited

Message:

AIE PBT 30G8F is a polybutene terephthalate (PBT) material, which contains a filler of 40% glass fabric reinforcement. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is injection molding.

The main features of AIE PBT 30G8F are:

- flame retardant/rated flame
- Flame Retardant
- Hard
- Good dimensional stability

General Information			
Filler / Reinforcement	Glass fabric reinforced material, 40% filler by weight		
Features	Good dimensional stability		
	Rigidity, high		
	Flame retardancy		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.73	g/cm ³	ISO 1183
Molding Shrinkage	0.20 - 0.30	%	Internal method
Water Absorption (23°C, 24 hr)	0.30	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	140	MPa	ISO 527-2
Tensile Strain (Break)	0.80	%	ISO 527-2
Flexural Modulus	9500	MPa	ISO 178
Flexural Stress	195	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	18	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	225	°C	ISO 75-2/B
1.8 MPa, not annealed	212	°C	ISO 75-2/A
Flammability	Nominal Value	Test Method	
Flame Rating (0.800 mm)	V-0	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	100 - 140	°C	
Drying Time	4.0 - 6.0	hr	
Rear Temperature	235 - 250	°C	
Middle Temperature	240 - 260	°C	

Front Temperature	240 - 260	°C
Nozzle Temperature	230 - 245	°C
Mold Temperature	50.0 - 160	°C
Injection Pressure	40.0 - 120	MPa
Holding Pressure	40.0 - 50.0	MPa
Back Pressure	5.00 - 10.0	MPa
Screw Speed	40 - 75	rpm

Injection instructions

Cylinder Temperature 4: 190 to 220°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

