

# Exelene® PS 6200

General Purpose Polystyrene

Montachem International, Inc.

## Message:

Applications:

Foam Disposables, Insulation Foam Board, OPS Disposables

Characteristics:

The Exelene resin GPPS 6200 meets the requirements of section 177.1640, paragraph C, from chapter 21 denominated "Olefin Polymers" from the Code of Federal Regulations of the FDA, to be utilized with direct food contact.

General Information			
Features	Disposable		
	Food Contact Acceptable		
	General Purpose		
Uses	Disposable Drinkware		
	Foamed Insulation Board		
	Food Service Applications		
	General Purpose		
	Non-specific Food Applications		
Agency Ratings	FDA 21 CFR 177.1640		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.00	g/cm <sup>3</sup>	
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.6	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40 to 0.70	%	ASTM D955
Water Absorption (Saturation)	< 0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	52.4	MPa	ASTM D638
Flexural Strength	97.9	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	107	°C	ASTM D1525
Heat Deflection Temperature - Annealed	100	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: [sales@su-jiao.com](mailto:sales@su-jiao.com)

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

