

4LEX® 9F22110 FR1

Polycarbonate
4Plas

Message:

4LEX 9F22110 FR1 is a Standard Flow 10% Glass Fibre Reinforced FR-V0 Polycarbonate

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.29	g/cm ³	ISO 1183
Molding Shrinkage			
Vertical flow direction	0.50	%	
Flow direction	0.50	%	
Water Absorption ¹ (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Moisture Content	< 1000	ppm	ISO 960
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	4000	MPa	ISO 527-2/5
Tensile Stress (Break, 23°C)	80.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	4.0	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180/1A
-30°C	9.0	kJ/m ²	ISO 180/1A
23°C	11	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	140	°C	ISO 75-2/B
1.8 MPa, not annealed	130	°C	ISO 75-2/A
Vicat Softening Temperature	140	°C	ISO 306/B
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Comparative Tracking Index	175	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	V-0		UL 94
1.60 mm	V-0		UL 94
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (2.00 mm)	900	°C	IEC 60695-2-13

Injection	Nominal Value	Unit
Drying Temperature	120	°C
Drying Time	3.0 - 4.0	hr
Suggested Max Moisture	0.020	%
Processing (Melt) Temp	270 - 310	°C
Mold Temperature	80.0 - 120	°C
Injection Rate	Moderate-Fast	
Holding Pressure	60.0 - 120	MPa
Screw Speed	200	rpm

Injection instructions

Feed Throat Temperature: 60 - 80 °C Back Pressure: Low

NOTE

1. 24 Hrs

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

