

RTP 399 X 115069 D

Polycarbonate
RTP Company

Message:

Carbon Nanotube - Electrically Conductive - ESD Protection

General Information			
Filler / Reinforcement	Carbon nano filler		
Features	Conductivity		
	Electrostatic discharge protection		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.60 - 0.80	%	ASTM D955
Moisture Content	0.020	%	
Static Decay ¹		sec	FTMS 101C 4046.1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2070	MPa	ASTM D638
Tensile Strength	53.8	MPa	ASTM D638
Tensile Elongation (Yield)	> 8.0	%	ASTM D638
Flexural Modulus	2410	MPa	ASTM D790
Flexural Strength	89.6	MPa	ASTM D790
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity			
--	1.0E+5 - 1.0E+7	ohms	ASTM D257
--	1.0E+4 - 1.0E+6	ohms	ESD STM11.11
Volume Resistivity	10 - 1.0E+3	ohms · cm	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Dew Point	-28.9	°C	
Processing (Melt) Temp	288 - 316	°C	
Mold Temperature	82.2 - 121	°C	
Injection Pressure	68.9 - 103	MPa	
Injection instructions			
Desiccant Type Dryer Required.			
NOTE			

-
- | | |
|----|--|
| 1. | MIL-PRF-81705D, 5kV to 50 V, 12%
RH |
|----|--|

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

