# Abstron IM21M

### Acrylonitrile Butadiene Styrene

Bhansali Engineering Polymers Limited

#### Message:

Abstron IM21M is an Acrylonitrile Butadiene Styrene (ABS) product. It can be processed by injection molding and is available in Asia Pacific. Characteristics include: Flame Rated Impact Resistant Rigid

| General Information  |                          |          |             |
|--|--------------------------|----------|-------------|
| Features   | Medium Flow              |          |             |
|  | Medium Impact Resistance |          |             |
|  | Medium Rigidity          |          |             |
| Processing Method  | Injection Molding        |          |             |
| Physical   | Nominal Value            | Unit     | Test Method |
| Specific Gravity   | 1.04                     | g/cm³    | ASTM D792   |
| Melt Mass-Flow Rate (MFR) (220°C/10.0<br>kg)   | 32                       | g/10 min | ASTM D1238  |
| Molding Shrinkage - Flow   | 0.40 to 0.60             | %        | ASTM D955   |
| Hardness   | Nominal Value            | Unit     | Test Method |
| Rockwell Hardness (R-Scale, Injection<br>Molded)   | 113                      |          | ASTM D785   |
| Mechanical   | Nominal Value            | Unit     | Test Method |
| Tensile Strength <sup>1</sup> (Yield, 3.20 mm,<br>Injection Molded)                      | 48.1                     | MPa      | ASTM D638   |
| Flexural Modulus <sup>2</sup> (6.40 mm, Injection<br>Molded)                             | 2350                     | МРа      | ASTM D790   |
| Flexural Strength <sup>3</sup> (6.40 mm, Injection<br>Molded)                            | 70.6                     | МРа      | ASTM D790   |
| Impact   | Nominal Value            | Unit     | Test Method |
| Notched Izod Impact  |                          |          | ASTM D256   |
| 23°C, 3.20 mm, Injection Molded  | 210                      | J/m      |             |
| 23°C, 6.40 mm, Injection Molded  | 170                      | J/m      |             |
| Thermal  | Nominal Value            | Unit     | Test Method |
| Deflection Temperature Under Load <sup>4</sup> (1.8<br>MPa, Annealed, 6.40 mm, Injection |                          |          |             |
| Molded)  | 95.0                     | °C       | ASTM D648   |
| Flammability   | Nominal Value            |          | Test Method |
| Flame Rating (3.20 mm)   | НВ                       |          | UL 94       |
| NOTE   |                          |          |             |
| 1.   | Type I, 5.0 mm/min       |          |             |
| 2.   | 5.0 mm/min               |          |             |

| 3. | 5.0 mm/min                |
|----|---------------------------|
| 4. | Annealed at 85°C for 2 hr |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

