

FERREX® GPP20CK14HB-GY

Polypropylene

Ferro Corporation

Message:

FERREX® GPP20CK14HB-GY is a Polypropylene material filled with 20% calcium carbonate. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Important attributes of FERREX® GPP20CK14HB-GY are:

High Gloss

Impact Modified

General Information			
Filler / Reinforcement	Calcium Carbonate,20% Filler by Weight		
Additive	Impact Modifier		
Features	High Gloss		
	Impact Modified		
Appearance	Grey		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.06	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow	1.6	%	
Across Flow	1.8	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	26.2	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	35	%	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 23°C	1710	MPa	
Tangent : 23°C	1830	MPa	
Flexural Strength (23°C)	40.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	64	J/m	ASTM D256
Unnotched Izod Impact (23°C)	1000	J/m	ASTM D4812
Gardner Impact (23°C)	22.6	J	ASTM D5420
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	96.1	°C	
1.8 MPa, Unannealed	55.6	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

