

PENTAMID A S MK30 H FR natural

Polyamide 66
PENTAC Polymer GmbH

Message:
Low viscosity, heat stabilised polyamide 66, 30% mineral filled, flame retardant

General Information			
Filler / Reinforcement	Mineral filler, 30% filler by weight		
Additive	heat stabilizer		
	Flame retardancy		
Features	Low viscosity		
	Thermal Stability		
	Flame retardancy		
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.44	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Transverse flow	1.5	%	ISO 294-4
Flow	1.5	%	ISO 294-4
Water Absorption			ISO 62
Saturated, 23°C	4.9	%	ISO 62
Equilibrium, 23°C, 50% RH	1.6	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7000	MPa	ISO 527-2/1
Tensile Stress (Break)	70.0	MPa	ISO 527-2/5
Tensile Strain (Break)	2.0	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	30	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	235	°C	ISO 75-2/B
1.8 MPa, not annealed	110	°C	ISO 75-2/A
Melting Temperature	260	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method

Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Burning Rate	< 100	mm/min	FMVSS 302
Flame Rating (0.8 mm)	V-0		UL 94
Glow Wire Flammability Index (0.8 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (0.8 mm)	825	°C	IEC 60695-2-13
Additional Information	Nominal Value		Test Method
ISO Shortname	PA66, MFHR, 12-070, MD30 (FR)		ISO 1874
Injection	Nominal Value	Unit	
Drying Temperature	80	°C	
Drying Time	3.0	hr	
Suggested Max Moisture	0.050 - 0.13	%	
Suggested Max Regrind	20	%	
Rear Temperature	270 - 290	°C	
Middle Temperature	275 - 300	°C	
Front Temperature	280 - 290	°C	
Processing (Melt) Temp	270 - 300	°C	
Mold Temperature	60 - 100	°C	
Injection Pressure	78.0	MPa	
Screw L/D Ratio	18.0:1.0 to 22.0:1.0		
Screw Compression Ratio	2.2:1.0 to 2.8:1.0		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT