

Hostacom TKC 199N

Polypropylene Copolymer

LyondellBasell Industries

Message:

"Hostacom TKC 199N is a 20% mineral filled, polypropylene copolymer for injection molding. It combines excellent stiffness/impact balance, good scratch resistance, low odor and excellent flowability properties with good dimensional stability. The grade has been specifically designed for molding of automotive interior trim parts. The grade is available in color-matched, pellet form.

General Information			
Filler / Reinforcement	Mineral,20% Filler by Weight		
Features	Good Dimensional Stability Good Flow Good Impact Resistance Good Stiffness Low to No Odor Scratch Resistant		
Uses	Automotive Interior Parts		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.06	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	11	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - Secant	2250	MPa	ISO 527-2
Tensile Stress (Yield)	23.0	MPa	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	3.0	kJ/m ²	
23°C	35	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	100	°C	ISO 75-2/B
1.8 MPa, Unannealed	57.0	°C	ISO 75-2/A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

