TYRIN™ 7000

Chlorinated Polyethylene Resin

The Dow Chemical Company

Message:

TYRIN™7000 is a kind of chlorinated polyethylene with high viscosity and low crystallinity. This product is applied to the impact modification of hard PVC used in profiles, sheets and pipes. The product is supplied in the form of flowable powder and can be processed as bulk material. One of the advantages of this product is to improve the impact strength.

| General Information | | | |
|---|---------------|-------|-----------------|
| Forms | Powder | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 1.15 | g/cm³ | ISO 1183 |
| Apparent Density | 0.39 | g/cm³ | Internal method |
| Chlorine Content | 35.0 | wt% | ISO 1158 |
| Oil Type (soybean oil) | 3.0 | phr | Internal method |
| Ash Content | | % | ISO 247 |
| Volatile Matter | | % | ISO 248 |
| Average Particle Size | 250 | μm | ISO 2591-1 |
| Heat of Fusion | | J/g | Internal method |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Stress ¹ (100% Strain) | 1.60 | MPa | ISO 37 |
| Fill Analysis | Nominal Value | Unit | Test Method |
| Melt Viscosity | 2900 | Pa·s | ISO 11443 |
| Additional Information | | | |
| 数据涉及以下配方: TYRIN CPE 树脂:100 个零件 | | | |
| 硬脂酸钙:2 phr 硬脂酸:0.5 phr | | | |

硬脂酸:0.5 phr

环氧化豆油:3 phr

NOTE

1.

Formula adopted

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

